

## **AMENDMENT TO THE CLAIMS**

The following claim set replaces all prior versions, and listings, of claims in the application:

1. (Currently Amended) An amorphous wholly aromatic polyester amide of exhibiting optical anisotropy at the softening and flowing, which is a wholly aromatic polyester amide obtained by copolymerizing:

- (A) 4-hydroxybenzoic acid,
- (B) 2-hydroxy-6-naphthoic acid,
- (C) p-aminophenol; and
- (D) isophthalic acid as an aromatic dicarboxylic acid, wherein
  - (1) the ratio of (C) the p-aminophenol is from 7 to 35% by mol,
  - (2) the ratio of isophthalic acid as a bending monomer among starting material monomers is from 7 to 35% by mol,
  - (3) the ratio ((A)/(B)) between (A) the 4-hydroxybenzoic acid and (B) the 2-hydroxy-6-naphthoic acid is from 0.15 to 4.0,
  - ~~(4) the ratio of isophthalic acid is at least 35% by mol or more in (D) the aromatic dicarboxylic acid,~~
  - (4) ~~(5)~~ a melting point is not observed by DSC measurement at a temperature rising rate of 20°C/min and
  - (5) ~~(6)~~ the glass transition temperature is from 100 to 180°C.

2. - 5. (cancelled)

6. (previously presented) A fiber formed from the amorphous wholly aromatic polyester amide as claimed in claim 1.

7. (previously presented) A film or sheet formed from the amorphous wholly aromatic polyester amide as claimed in claim 1.

8. (previously presented) A multilayer film or multilayer sheet formed from the amorphous wholly aromatic polyester amide as claimed in claim 1 and another polymer.
9. (original) The multilayer film or multilayer sheet as claimed in claim 8, wherein the another polymer is polyolefin.
10. (previously presented) A blow molded article formed from the amorphous wholly aromatic polyester amide as claimed in claim 1.
11. (previously presented) A multilayer blow molded article formed from the amorphous wholly aromatic polyester amide as claimed in claim 1 and another polymer.
12. (original) The multilayer blow molded article as claimed in claim 11, wherein the another polymer is polyolefin.
13. (original) The multilayer blow molded article as claimed in claim 12, wherein the polyolefin is a high density polyethylene.
14. (previously presented) The blow molded article as claimed in claim 11, wherein the blow molded article is a fuel tank.